

# Coexistence of Superconductivity and Ferromagnetism in Superconducting $\text{HoMo}_6\text{S}_8$

Tadesse Desta<sup>1</sup>, Gebregziabher Kahsay<sup>2</sup>

<sup>1</sup>Department of Physics, Addis Ababa University, Addis Ababa, Ethiopia

<sup>2</sup>Department of Physics, College of Science, Bahir Dar University, Bahir Dar, Ethiopia

Email: [tad4ju@gmail.com](mailto:tad4ju@gmail.com), [michige\\_90@yahoo.com](mailto:michige_90@yahoo.com)

Received 29 January 2015; accepted 13 February 2015; published 16 February 2015

Copyright © 2015 by authors and Scientific Research Publishing Inc.

This work is licensed under the Creative Commons Attribution International License (CC BY).

<http://creativecommons.org/licenses/by/4.0/>



Open Access

---

## Abstract

This work focuses on the theoretical investigation of the coexistence of superconductivity and ferromagnetism in the superconducting  $\text{HoMo}_6\text{S}_8$ . By developing a model Hamiltonian for the system and using the Green's function formalism and equation of motion method, we have obtained expressions for superconducting transition temperature ( $T_c$ ), magnetic order temperature ( $T_m$ ), superconductivity order parameter ( $\Delta$ ) and magnetic order parameter ( $\eta$ ). By employing the experimental and theoretical values of the parameters in the obtained expressions, phase diagrams of energy gap parameter versus transition temperature, superconducting transition temperature versus magnetic order parameter and magnetic order temperature versus magnetic order parameter are plotted separately. By combining the phase diagrams of superconducting transition temperature versus magnetic order parameter and magnetic order temperature versus magnetic order parameter, we have demonstrated the possible coexistence of superconductivity and ferromagnetism in superconducting  $\text{HoMo}_6\text{S}_8$ .

## Keywords

Superconductivity, Ferromagnetism, Coexistence, Green's Function,  $\text{HoMo}_6\text{S}_8$

---

## 1. Introduction

Superconductivity was discovered in 1911 by Kamerlingh Onnes [1] when a so-called “Blue Boy” noticed that the resistivity of Hg metal vanished abruptly at a temperature of about 4.2 K. Ferromagnetism is a phenomenon by which a material can exhibit a spontaneous magnetization and is one of the strongest forms of magnetism. It

is responsible for most of the magnetic behaviors encountered in everyday life and is the basis for all permanent magnets (as well as the metals that are noticeably attracted to them). In particular, a material is ferromagnetic in narrower sense only if all of its magneticians add a positive contribution to the net magnetization. If some of the magneticians subtract from the net magnetization, that is, if they are partially anti-aligned, then the material is ferrimagnetic. If the ions anti-align completely so as to have zero netmagnetization, despite the magnetic ordering, then it is an antiferromagnet. Thus, ferromagnetic materials exhibit parallel alignment of moments resulting in large net magnetization even in the absence of a magnetic field.

Superconductivity in Ferromagnetic must result from a different type of electronpairing mechanisms. In these materials, electrons with spins pointing in the same direction team up with each other to form Cooper pairs with one unit of spin resulting in a triplet superconductivity. In contrast, conventional superconductivity also known as s-wave singlet superconductivity occurs when electrons with oppositespins bind together to form Cooper pairs with zero momentum and spin.

The coexistence of superconductivity and ferromagnetism has been studied theoretically and experimentally. The coexistence of ferromagnetism and superconductivity was first addressed theoretically by Ginzburg in 1957 [2] and experimental investigation was made by Matthias *et al.* [3]. The interplay between superconducting and ferromagnetic long range order has been recently attracting new interest due to the discovery of superconductivity in ferromagnetic compounds such as UGe<sub>2</sub> [4], URhGe [5], ZrZn<sub>2</sub> [6], and in RuSr<sub>2</sub>RECu<sub>2</sub>O<sub>8</sub> compounds (with RE = Eu or Gd) [7]. The relationship between magnetism and superconductivity has received renewed attention since the discovery of ternary superconducting materials which also achieved long-range magnetic ordering at low temperatures. Ferromagnetic alignment can be expected to be strongly opposed by superconductivity. Such a long-period magnetic ordering was actually found in HoMo<sub>6</sub>S<sub>8</sub> and in ErRh<sub>4</sub>B<sub>4</sub>. In ErRh<sub>4</sub>B<sub>4</sub>, Sinha *et al.* [8] carried out a detailed study on a single crystal in order to characterize this phase. For HoMo<sub>6</sub>S<sub>8</sub>, the study was done by Lynn *et al.* [9] only on polycrystalline samples.

In HoMo<sub>6</sub>S<sub>8</sub>, the ferromagnetic state destroys the superconductivity at sufficiently low temperatures. Recently, an experiment on HoMo<sub>6</sub>S<sub>8</sub> [10] has shown that, the superconducting ordering parameter has a distinct maximum between some critical temperatures  $T_{c1}$  and  $T_{c2}$  (lower and upper superconducting critical temperatures), respectively and vanishes for  $T < T_{c1}$  and  $T > T_{c2}$ .

Among the “Chevrel phases”, HoMo<sub>6</sub>S<sub>8</sub> has been extensively studied in recent years [11]. HoMo<sub>6</sub>S<sub>8</sub> becomes superconducting at  $T_{c1} \cong 1.82$  K, but at a lower temperature  $T_{c2} \cong 0.64$  K, it re-enters the normal state at the onset of long range ferromagnetic order. In a narrow temperature range  $T_{c2} < T < T_m$ , superconductivity coexists with a modulated magnetic structure [12].

## 2. Model System Hamiltonian

In order to study the coexistence of ferromagnetism and superconductivity in superconducting HoMo<sub>6</sub>S<sub>8</sub> theoretically in general and to find the expressions for transition temperature and order parameters in particular, a system of conduction and localized electrons have been considered. The exchange interaction acts between the conduction and the localized electrons. Thus, within the frame work of the BCS model [13], the model system Hamiltonian can be formulated as follows.

$$\hat{H} = \hat{H}_1 + \hat{H}_2 + \hat{H}_3 \quad (1)$$

where

$$\hat{H}_1 = \sum_{\kappa, \sigma} \epsilon_{\kappa} \hat{a}_{\kappa, \sigma}^{\dagger} \hat{a}_{\kappa, \sigma} + \sum_{l, \sigma} \epsilon_l \hat{b}_{l, \sigma}^{\dagger} \hat{b}_{l, \sigma} \quad (2)$$

and is the Hamiltonian or energy of mobile (conduction) electrons and localized electrons respectively.

Here, the operators  $\hat{a}_{\kappa, \sigma}^{\dagger}$  ( $\hat{a}_{\kappa, \sigma}$ ) and  $\hat{b}_{l, \sigma}^{\dagger}$  ( $\hat{b}_{l, \sigma}$ ) are the creation (annihilation) operators for conduction and localized electrons respectively with the wave vector  $\kappa$  and the spin projection on z-axis  $\sigma = \uparrow$  or  $\downarrow$ .  $\epsilon_{\kappa}$  is the one electron kinetic energy measured relative to the chemical potential.  $\hat{H}_2$  is the interaction (electron-electron) through boson (phonon) exchange and is given by,

$$\hat{H}_2 = -\sum_{\kappa, \kappa'} V_{\kappa \kappa'} \hat{a}_{\kappa \uparrow}^{\dagger} \hat{a}_{\kappa' \uparrow}^{\dagger} \hat{a}_{-\kappa' \uparrow} \hat{a}_{\kappa \uparrow} \quad (3)$$

where  $V_{\kappa \kappa'}$  defines the matrix element of the interaction potential.  $\hat{H}_3$  is the interaction term between con-

duction electrons and localized electrons due to some unspecified mechanism with some coupling constant ( $\alpha$ ) and is expressed as,

$$\hat{H}_3 = \sum_{l,m,\kappa} \alpha_{l,m} \hat{a}_{\kappa\uparrow}^\dagger \hat{a}_{-\kappa\uparrow}^\dagger \hat{b}_{l\uparrow} \hat{b}_{m\uparrow} + h.c. \quad (4)$$

### 3. Equation of Motion for Mobile (Conduction) Electrons

Now, let us evaluate the following commutation relation,

$$[\hat{a}_{\kappa\uparrow}, \hat{H}] = [\hat{a}_{\kappa\uparrow}, \hat{H}_1] + [\hat{a}_{\kappa\uparrow}, \hat{H}_2] + [\hat{a}_{\kappa\uparrow}, \hat{H}_3]. \quad (5)$$

From which we obtain,

$$[\hat{a}_{\kappa\uparrow}, \hat{H}_1] = [\hat{a}_{\kappa\uparrow}, \sum_{p,\sigma} \epsilon_p \hat{a}_{p,\sigma}^\dagger \hat{a}_{p,\sigma} + \sum_{l,\sigma} \epsilon_l \hat{b}_{l,\sigma}^\dagger \hat{b}_{l,\sigma}] = \epsilon_\kappa \hat{a}_{\kappa\uparrow}. \quad (6)$$

Following similar procedure as above, we get,

$$[\hat{a}_{\kappa\uparrow}, \hat{H}_2] = -\sum_{p'} V_{\kappa p'} \hat{a}_{-\kappa\uparrow}^\dagger \hat{a}_{-p'\uparrow} \hat{a}_{p'\uparrow} \quad (7)$$

and

$$[\hat{a}_{\kappa\uparrow}, \hat{H}_3] = \sum_{l,m} \alpha_{l,m} \hat{a}_{-\kappa\uparrow}^\dagger \hat{b}_{l\uparrow} \hat{b}_{m\uparrow}. \quad (8)$$

Substituting Equations (6), (7) and (8) into the equation of motion given by,

$$\omega \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa'\downarrow}^\dagger \rangle \rangle_\omega = \delta_{\kappa\kappa'} + \langle \langle [\hat{a}_{\kappa\uparrow}, \hat{H}_{BCS}] ; \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle_\omega \quad (9)$$

we obtain,

$$\omega \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle = 1 + \epsilon_\kappa \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle - \sum_{p'} V_{p\kappa'} \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger \hat{a}_{-p'\uparrow} \hat{a}_{p'\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle + \sum_{l,m} \alpha_{l,m} \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger \hat{b}_{l\uparrow} \hat{b}_{m\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle. \quad (10)$$

In general, we have to write the higher order Green's function into lower order Green's function by using Wick's theorem. Thus, we have,

$$\langle \langle \hat{a}_{-\kappa\uparrow}^\dagger \hat{a}_{-p'\uparrow} \hat{a}_{p'\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle = \langle \hat{a}_{p'\uparrow} \hat{a}_{-p'\uparrow} \rangle \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle. \quad (11)$$

Now, substituting Equation (11) into Equation (10), we get,

$$\begin{aligned} (\omega - \epsilon_\kappa) \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle &= 1 - \sum_{p'} V_{pp'} \langle \hat{a}_{-p'\uparrow} \hat{a}_{p'\uparrow} \rangle \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle + \sum_{l,m,p} \alpha_{l,m} \langle \hat{b}_{l\uparrow} \hat{b}_{m\uparrow} \rangle \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle \\ (\omega - \epsilon_\kappa) \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle &= 1 - (\Delta - \eta) \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle \end{aligned} \quad (12)$$

where  $\Delta = \sum_{p'} V_{pp'} \langle \hat{a}_{-p'\uparrow} \hat{a}_{p'\uparrow} \rangle$  and  $\eta = \sum_{l,m,p} \alpha_{l,m} \langle \hat{b}_{l\uparrow} \hat{b}_{m\uparrow} \rangle$ .

One can also obtain the equation of motion for the expression  $\langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle$  and obtain,

$$\omega \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle = -\epsilon_{-\kappa} \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle - \sum_{p'} V_{pp'} \langle \hat{a}_{p'\uparrow}, \hat{a}_{-p'\uparrow}^\dagger \rangle \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle + \sum_{l,m} \alpha_{l,m} \langle \hat{b}_{l\uparrow} \hat{b}_{m\uparrow} \rangle \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle. \quad (13)$$

For  $\epsilon_\kappa = \epsilon_{-\kappa}$ ,  $\Delta = \Delta^*$  and  $\eta = \eta^*$ , we obtain,

$$(\omega + \epsilon_\kappa) \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle = -(\Delta - \eta) \langle \langle \hat{a}_{\kappa\uparrow}, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle. \quad (14)$$

Now, using Equations (12) and (14), the equation of motion becomes,

$$(\omega + \epsilon_\kappa) \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle = \frac{-(\Delta - \eta)}{\omega - \epsilon_\kappa} + \frac{(\Delta - \eta)^2}{\omega - \epsilon_\kappa} \langle \langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle \rangle.$$

From which we obtain,

$$\langle\langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle\rangle = \frac{-(\Delta - \eta)}{(\omega^2 - \epsilon_\kappa^2 - (\Delta - \eta)^2)}. \quad (15)$$

Using the relation for  $\Delta$ , given by,

$$\Delta = \frac{V}{\beta} \sum_\kappa \langle\langle \hat{a}_{-\kappa\uparrow}^\dagger, \hat{a}_{\kappa\uparrow}^\dagger \rangle\rangle \quad (16)$$

and by changing the summation into integration and by introducing the density of states at the Fermi level,  $N(0)$ , we get,

$$\Delta = -\frac{1}{\beta} \int_{-\epsilon_F}^{\infty} N(0) V \frac{(\Delta - \eta)}{(\omega^2 - \epsilon^2 - (\Delta - \eta)^2)} d\epsilon. \quad (17)$$

Now, changing  $\omega \rightarrow i\omega_n$ , we use the Matsubara frequency [14],

$$\omega_n = (2n+1) \frac{\pi}{\beta}. \quad (18)$$

Now, using Equation (18) in Equation (17), we get,

$$\hbar\omega_b = 2N(0)V\beta \sum_n \int_0^{\hbar\omega_b} \left[ \frac{(\Delta - \eta)}{(2n+1)^2 \pi^2 + \beta^2 E^2} \right] d\epsilon, \quad (19)$$

where  $E^2 = \epsilon_\kappa^2 + (\Delta - \eta)^2$ . Since attraction is effective in the region  $-\hbar\omega_b < \epsilon < \hbar\omega_b$ , and taking the density of state to be constant in this region and using the relation,

$$\frac{1}{2x} \tanh\left(\frac{x}{2}\right) = \sum_{n=-\infty}^{+\infty} \frac{1}{(2n+1)^2 \pi^2 + x^2}.$$

We can write Equation (19) as,

$$\Delta = 2N(0)V\beta \int_0^{\hbar\omega_b} (\Delta - \eta) \frac{1}{2\beta E} \tanh(\beta E/2) d\epsilon. \quad (20)$$

Let  $\lambda = N(0)V$ ,

$$\frac{\Delta}{\lambda} = \int_0^{\hbar\omega_b} \frac{(\Delta - \eta)}{\sqrt{(\epsilon^2 + (\Delta - \eta)^2)}} \tanh\left(\beta \sqrt{\epsilon^2 + (\Delta - \eta)^2} / 2\right) d\epsilon. \quad (21)$$

### 3.1. Effect of Temperature on Superconducting Order Parameter ( $\Delta$ ) and Magnetic Order Parameter ( $\eta$ )

Now, let us study equation (21) by considering different cases.

**Case (I):** As  $T \rightarrow 0$  K,  $\beta \Rightarrow \infty$ , so that,  $\tanh(\beta E/2) \rightarrow 1$ .

Hence, Equation (21) becomes,

$$\frac{\Delta}{\lambda} = \int_0^{\hbar\omega_b} \frac{(\Delta - \eta)}{\sqrt{(\epsilon^2 + (\Delta - \eta)^2)}} d\epsilon. \quad (22)$$

Using the integral  $\int \frac{a}{\sqrt{a^2 + x^2}} dx = a \sinh^{-1}\left(\frac{x}{a}\right)$ , where  $a = \Delta - \eta$ , Equation (21) becomes,

$$\frac{1}{\lambda} = \left(1 - \frac{\eta}{\Delta}\right) \sinh^{-1}\left(\frac{\epsilon}{\Delta - \eta}\right) \Bigg|_0^{\hbar\omega_b} = \left(1 - \frac{\eta}{\Delta}\right) \sinh^{-1}\left(\frac{\hbar\omega_b}{\Delta - \eta}\right) \quad (23)$$

$$\frac{1}{\lambda} \approx \left(1 - \frac{\eta}{\Delta}\right) \ln \left\{ \frac{\hbar\omega_b}{\Delta - \eta} + \sqrt{\left(\frac{\hbar\omega_b}{\Delta - \eta}\right)^2 + 1} \right\}. \quad (24)$$

For  $\left(\frac{\hbar\omega_b}{\Delta - \eta}\right)^2 \gg 1$ , Equation (24) reduces to,

$$\frac{1}{\lambda} \approx \left(1 - \frac{\eta}{\Delta}\right) \ln \left(\frac{2\hbar\omega_b}{\Delta - \eta}\right). \quad (25)$$

This implies that,

$$\Delta - \eta = 2\hbar\omega_b \exp \left[ -\frac{1}{\lambda \left(1 - \frac{\eta}{\Delta}\right)} \right]. \quad (26)$$

For  $\eta = 0$ , Equation (26) reduces to the well-known BCS model.

The experimental value of  $\text{HoMo}_6\text{S}_8$  is,  $T_c \approx 1.82$  K.

Thus,  $\Delta(0) = 1.75k_B T_c \cong 4.39 \times 10^{-23}$  J, where  $\hbar\omega_b = \hbar\omega_D = 10^{-3}$  eV (for BCS model).


**Case (II):** At  $T = T_c$ ,  $\Delta = 0$ . Thus, we get,

$$\eta = 1.75k_B T_c - 2\hbar\omega_b \exp \left[ -\frac{1}{\lambda \left(1 - \frac{\eta}{\Delta(0)}\right)} \right]. \quad (27)$$

Now, employing Equation (27) and the experimental value of  $T_c$  for the superconducting  $\text{HoMo}_6\text{S}_8$  and plausible approximations for other parameters, we plotted the transition temperature ( $T_c$ ) versus magnetic ordering parameter ( $\eta$ ) as shown in [Figure 1](#).

For  $\eta = 0$ , we get the expression for  $T_c$  to be,

$$T_c = \frac{1.14\hbar\omega_b}{k_B} \exp \left( -\frac{1}{\lambda} \right). \quad (28)$$



**Figure 1.** Transition temperature ( $T_c$ ) versus magnetic order parameter ( $\eta$ ) for superconducting  $\text{HoMo}_6\text{S}_8$ .

### 3.2. Equation of Motion for Localized Electrons

Using Green's function formalism, the equation of motion for the localized electrons is obtained to be,

$$\omega \langle \langle \hat{b}_{l\uparrow}, \hat{b}_{l\uparrow}^\dagger \rangle \rangle = 1 + \langle \langle [\hat{b}_{l\uparrow}, \hat{H}]; \hat{b}_{l\uparrow}^\dagger \rangle \rangle. \quad (29)$$

Now, using the Hamiltonian given in Equation (1), we evaluated the commutation  $[\hat{b}_{l\uparrow}, H]$  and obtained,

$$\omega \langle \langle \hat{b}_{l\uparrow}, \hat{b}_{l\uparrow}^\dagger \rangle \rangle_\omega = 1 + \epsilon_l \langle \langle \hat{b}_{l\uparrow}, \hat{b}_{l\uparrow}^\dagger \rangle \rangle + \sum_{\kappa, m} \alpha_{l, m} \langle \langle \hat{a}_{-\kappa\uparrow} \hat{a}_{\kappa\uparrow} \hat{b}_{m\uparrow}^\dagger, \hat{b}_{l\uparrow}^\dagger \rangle \rangle \quad (30)$$

$$\langle \langle \hat{b}_{l\uparrow}, \hat{b}_{l\uparrow}^\dagger \rangle \rangle = \frac{1}{(\omega - \epsilon_l)} + \frac{\Delta_l}{(\omega - \epsilon_l)} \langle \langle \hat{b}_{m\uparrow}^\dagger, \hat{b}_{l\uparrow}^\dagger \rangle \rangle \quad (31)$$

where  $\Delta_l = \sum_{\kappa, m} \alpha_{l, m} \langle \hat{a}_{-\kappa\uparrow} \hat{a}_{\kappa\uparrow} \rangle$ .

Applying similar procedure as above and assuming  $\epsilon_l = \epsilon_m$ , we can obtain the expression for  $\langle \langle \hat{b}_{m\uparrow}^\dagger, \hat{b}_{l\uparrow}^\dagger \rangle \rangle$  to be,

$$\langle \langle \hat{b}_{m\uparrow}^\dagger, \hat{b}_{l\uparrow}^\dagger \rangle \rangle = \frac{\Delta_l}{(\omega + \epsilon_l)} \langle \langle \hat{b}_{l\uparrow}, \hat{b}_{l\uparrow}^\dagger \rangle \rangle. \quad (32)$$

Now, from Equations (31) and (32), we get,

$$\langle \langle \hat{b}_{m\uparrow}^\dagger, \hat{b}_{l\uparrow}^\dagger \rangle \rangle = \frac{\Delta_l}{(\omega^2 - \epsilon_l^2 - \Delta_l^2)}. \quad (33)$$

From which we get,

$$\langle \langle \hat{b}_{l\uparrow}, \hat{b}_{l\uparrow}^\dagger \rangle \rangle = \frac{(\omega + \epsilon_l)}{(\omega^2 - \epsilon_l^2 - \Delta_l^2)}. \quad (34)$$

### 3.3. Correlation between Conduction and Mobile Electrons

The equation of motion that shows the correlation between the conduction and localized electrons can be demonstrated. Using similar definition as for  $\Delta$ , we can write the magnetic ordering parameter,  $\eta$  as,

$$\eta = \frac{\alpha}{\beta} \sum_{\kappa, n} \langle \langle \hat{b}_{m\uparrow}^\dagger, \hat{b}_{l\uparrow}^\dagger \rangle \rangle = \frac{\alpha}{\beta} \sum_{\kappa, n} \frac{\Delta_l}{(\omega^2 - \epsilon_l^2 - \Delta_l^2)}. \quad (35)$$

Changing the summation into integration and by introducing the density of states,  $N(0)$ , we get,

$$\eta = \frac{2N(0)\alpha}{\beta} \sum_n \int_0^{\hbar\omega_b} \left( \frac{\Delta_l}{(\omega^2 - \epsilon_l^2 - \Delta_l^2)} \right) d\epsilon. \quad (36)$$

Using the Matsubara frequency,

$$\omega_n = \frac{(2n+1)\pi}{\beta} \quad \text{and} \quad \frac{1}{2x} \tanh(x/2) = \sum_n \frac{1}{(2n+1)^2 \pi^2 + x^2}.$$

Equation (36) becomes,

$$\eta = \lambda_l \int_0^{\hbar\omega_b} \frac{|\Delta_l|}{\sqrt{(\epsilon_l^2 + \Delta_l^2)}} \tanh\left(\beta \sqrt{(\epsilon_l^2 + \Delta_l^2)} / 2\right) d\epsilon, \quad (37)$$

where  $\lambda_l = N(0)\alpha$  and  $E^2 = \epsilon_l^2 + \Delta_l^2$ .

Now, let us first solve the following expression.

$$\int_0^{\hbar\omega_b} \frac{1}{\sqrt{(\epsilon_l^2 + \Delta_l^2)}} \tanh\left(\beta\sqrt{(\epsilon_l^2 + \Delta_l^2)}/2\right) d\epsilon = \int_0^{\hbar\omega_b} \frac{2}{\beta} \sum_{n=-\infty}^{\infty} \frac{1}{\omega_n^2 + \epsilon^2 + \Delta_l^2} d\epsilon, \quad (38)$$

Using Laplace's transform and Matsubara frequency, Equation (38) becomes,

$$\int_0^{\hbar\omega_b} \frac{\tanh\left(\beta\sqrt{(\epsilon_l^2 + \Delta_l^2)}/2\right)}{\sqrt{(\epsilon_l^2 + \Delta_l^2)}} d\epsilon = \int_0^{\hbar\omega_b} \frac{\tanh(\beta\epsilon/2)}{\epsilon} d\epsilon - \int_0^{\hbar\omega_b} \Delta_l^2 \frac{4}{\beta} \sum_{n=0}^{\infty} \frac{1}{a^4(1+x^2)^2} d\epsilon = I_1 + I_2.$$

where

$$I_1 = \int_0^{\hbar\omega_b} \int_0^{\hbar\omega_b} \frac{\tanh(\beta\epsilon/2)}{\epsilon} d\epsilon = -\ln 1.14 \frac{\hbar\omega_b}{k_B T_m}, \quad (39)$$

and

$$I_2 = \int_0^{\hbar\omega_b} \Delta_l^2 \frac{4}{\beta} \sum_{n=0}^{\infty} \frac{1}{a^4(1+x^2)^2} d\epsilon + \dots \approx \left(\frac{\Delta_l}{\pi k_B T_m}\right)^2 1.05. \quad (40)$$

Then,

$$\eta \approx -\lambda_l \Delta_l \left( \ln \left( 1.14 \frac{\hbar\omega_b}{k_B T_m} \right) + \left( \frac{\Delta_l}{\pi k_B T_m} \right)^2 1.05 \right). \quad (41)$$


Since  $\Delta_l$  is very small,  $\Delta_l^3$  can be neglected and thus Equation (41) becomes,

$$\eta \approx -\lambda_l \Delta_l \ln 1.14 \frac{\hbar\omega_b}{k_B T_m}.$$

From which we get,

$$T_m = \frac{1.14}{k_B} \hbar\omega_b \exp\left(\frac{\eta}{\lambda_l \Delta_l}\right). \quad (42)$$

Using Equation (42) and the experimental value,  $T_m \approx 0.67$  K for  $\text{HoMo}_6\text{S}_8$  and some plausible approximations for other parameters in the equation, we plot the magnetic order temperature ( $T_m$ ) versus magnetic order parameter as shown in **Figure 2**.



**Figure 2.** Magnetic order temperature ( $T_m$ ) versus magnetic order parameter ( $\eta$ ) for superconducting  $\text{HoMo}_6\text{S}_8$ .

### 3.4. Equation of Motion for Pure Superconducting System

For pure superconducting system, that is, when magnetic order cannot appear or magnetic effect is zero, we can ignore  $\eta$  and our previous calculation gives the following results which is similar to the well-known BCS model.

As  $T \rightarrow 0$ ,  $\eta \rightarrow 0$  and  $\tanh(\beta E/2) \rightarrow 1$ , Equation (21) reduces to,

$$\frac{1}{\lambda} = \int_0^{\hbar\omega_b} \frac{1}{\sqrt{\epsilon^2 + \Delta^2}} d\epsilon = \sinh^{-1} \left( \frac{\hbar\omega_b}{\Delta} \right). \quad (43)$$

From which we obtain,

$$\Delta(0) \approx 2\hbar\omega_b e^{-\frac{1}{\lambda}}. \quad (44)$$

Furthermore, for  $T \rightarrow T_c$ ,  $\eta = 0$  and for low temperature, *i.e.*  $\tanh \left( \frac{\hbar\omega_b}{2k_B T} \right) \rightarrow 1$ , Equation (21) yields,

$$\frac{1}{\lambda} = \int_0^{\hbar\omega_b} \frac{1}{\epsilon_k} \tanh \left( \beta \frac{\epsilon_k}{2} \right) d\epsilon_k = \ln 1.14 \frac{\hbar\omega_b}{k_B T_c}.$$

From which we get,

$$k_B T_c = 1.14 \hbar\omega_b \exp \left( -\frac{1}{\lambda} \right). \quad (45)$$

To obtain the temperature dependency of energy gap in Equation (21), we used the same techniques to solve the integral,

$$\frac{1}{\lambda} = \int_0^{\hbar\omega_b} \left( \frac{1}{\sqrt{\epsilon^2 + \Delta^2}} \tanh \left( \beta \frac{\sqrt{\epsilon^2 + \Delta^2}}{2} \right) \right) d\epsilon = \ln 1.14 \frac{\hbar\omega_b}{k_B T} - \Delta^2 \left( \frac{1}{\pi k_B T} \right)^2 1.05 + \dots \quad (46)$$

But from the BCS model  $\frac{1}{\lambda} = \ln 1.14 \frac{\hbar\omega_b}{k_B T_c}$ , (as  $T \rightarrow T_c, \Delta \rightarrow 0$ ).

For  $\omega_b = \omega_D$ , Equation (46) can be simplified and obtain,

$$\ln(T/T_c) = -\Delta^2 \left( \frac{1}{\pi k_B T_c} \right)^2 1.05 + \dots$$

Using the relation  $\ln(1-x) = -x - x^2/2 + \dots$ , we get,

$$-(1-T/T_c) \approx \ln(T/T_c) = -\Delta^2 \left( \frac{1}{\pi k_B T_c} \right)^2 1.05 + \dots$$

From which we can get,

$$\Delta(T) = 3.06 k_B T_c (1-T/T_c)^{1/2}. \quad (47)$$

Equation (47) shows how the superconducting order parameter,  $\Delta(T)$  varies with temperature when  $\eta = 0$  and is similar to the BCS model.


Using the experimental value,  $T_c \approx 1.82$  K for  $\text{HoMo}_6\text{S}_8$  and some plausible approximations, we plot  $\Delta$  versus  $T_c$  as shown in [Figure 3](#).

Now, by combining [Figure 1](#) and [Figure 2](#), we demonstrated the possible coexistence of superconductivity and ferromagnetism in  $\text{HoMo}_6\text{S}_8$  as shown in [Figure 4](#).


## 4. Results and Discussion

In this section, we describe the results which are obtained using the model Hamiltonian developed. We obtain the expressions for the superconducting ordering parameter ( $\Delta$ ) and magnetic order parameter ( $\eta$ ) with respect to





**Figure 3.** Energy gap parameter ( $\Delta$ ) versus transition temperature ( $T_c$ ) for superconducting  $\text{HoMo}_6\text{S}_8$ .



**Figure 4.** Coexistence of superconductivity and ferromagnetism in superconducting  $\text{HoMo}_6\text{S}_8$ .

superconducting transition temperature ( $T_c$ ) and magnetic order temperature ( $T_m$ ) respectively. First, using Equation (27) and the experimental value of  $T_c$  for the superconducting  $\text{HoMo}_6\text{S}_8$  and plausible approximations for other parameters, we plotted the transition temperature ( $T_c$ ) versus magnetic order parameter ( $\eta$ ) as shown in **Figure 1**. As can be seen from the figure, when the magnetic order parameter increases the superconducting transition temperature decreases. Second, by employing Equation (42) and the experimental value,  $T_m \approx 0.67$  K for  $\text{HoMo}_6\text{S}_8$  and some suitable approximations for the other parameters in the equation, we plotted the magnetic order temperature versus magnetic order parameter as demonstrated in **Figure 2**. From the figure, it is vivid that, as the magnetic order parameter increases the magnetic order temperature also increases. Furthermore, the superconducting order parameter ( $\Delta$ ) is expressed as a function of the transition temperature ( $T_c$ ) and is plotted in **Figure 3**. The expression we obtained for the pure superconductor in Equation (47) is in agreement with the BCS model for  $\eta = 0$ . It is clear that from **Figure 3**, the superconducting order parameter, which is the measure of pairing energy decreases with increasing temperature and vanishes at the transition temperature ( $T_c$ ). From **Figure 4**, we observe that,  $T_c$  decreases with increasing  $\eta$ , whereas  $T_m$  increases with increasing  $\eta$  and there is a small region of temperature where both superconductivity and ferromagnetism coexist in  $\text{HoMo}_6\text{S}_8$ . Our finding is in agreement with the experimental observation [15].

## 5. Conclusion

In the present work, we have demonstrated the basic concepts of superconductivity with special emphasis on the BCS model and Cooper pair focusing on the interaction between superconductivity and ferromagnetism which are closely connected to the particular crystal of superconducting  $\text{HoMo}_6\text{S}_8$ . Employing the double time temperature dependent retarded Green's functions formalism, we developed the model Hamiltonian for the system and

derived equations of motion for conduction electrons, localized electrons and for pure superconducting system and carried out various correlations by using suitable decoupling procedures. In developing the model Hamiltonian, we considered spin triplet pairing mechanism and obtained expressions for superconducting order parameter, magnetic order parameter, superconducting transition temperature and magnetic order temperature. By using appropriate experimental values and considering suitable approximations, we plotted figures using the equations developed. As is well-known, superconductivity and ferromagnetism are two cooperative phenomena which are mutually antagonistic since superconductivity is associated with the pairing of electron states related to time reversal while in the magnetic states the time reversal symmetry is lost. Because of this, there is a strong competition between the two phases. This competition between superconductivity and magnetism made coexistence unlikely to occur. However, the model we employed in this work, shows that, there is a small region of temperature where both superconductivity and ferromagnetism can coexist in superconducting  $\text{HoMo}_6\text{S}_8$ .

## References

- [1] Onnes, H.K. (1911) *Akad. van Wetenschappen (Amsterdam)*, **14**, 113.
- [2] Ginzburg, V.L. (1957) Ferromagnetic Superconductors. *Soviet Physics—JETP*, **4**, 153.
- [3] Matthias, B.T., Suhl, H. and Corenzwit, E. (1958) Spin Exchange in Superconductors. *Physical Review Letters*, **1**, 92.  
<http://dx.doi.org/10.1103/PhysRevLett.1.92>
- [4] Saxena, S.S., Agarwal, P., Ahilan, K., Grosche, F.M., Haselwimmer, R.K.W., Steiner, M.J., Pugh, E., Walker, I.R., Julian, S.R., Monthoux, P., Lonzarich, G.G., Huxley, A., Sheikin, I., Braithwaite, D. and Flouquet, J. (2000) Superconductivity on the Border of Itinerant-Electron Ferromagnetism in  $\text{UGe}_2$  Superconductivity. *Nature*, **406**, 587.  
<http://dx.doi.org/10.1038/35020500>
- [5] Aoki, D., Huxley, A., Ressouche, E., Braithwaite, D., Flouquet, J., Brison, J.P., Lhote, E. and Paulsen, C. (2001) Coexistence of Superconductivity and Ferromagnetism in  $\text{URhGe}$ . *Nature*, **413**, 613-616.  
<http://dx.doi.org/10.1038/35098048>
- [6] Pfleiderer, C., Uhlarz, M., Hayden, S.M., Vollmer, R., Löhneysen, H.V., Bernhoeft, N.R. and Lonzarich, G.G. (2001) Coexistence of Superconductivity and Ferromagnetism in the d-Band Metal  $\text{ZrZn}_2$ . *Nature*, **412**, 58.  
<http://dx.doi.org/10.1038/35083531>
- [7] Cuoco, M., Gentile, P. and Noce, C. (2003) Coexistence of Ferromagnetism and Singlet Superconductivity via Kinetic Exchange. *Physical Review Letters*, **91**, Article ID: 197003. <http://dx.doi.org/10.1103/PhysRevLett.91.197003>
- [8] Sinha, S.K., Crabtree, G.W., Hinks, D.G., Mook, H.A. and Pringle, O.A. (1983) Neutron Scattering Studies of Magnetic Superconductors. *Journal of Magnetism and Magnetic Materials*, **31-34**, 489.  
[http://dx.doi.org/10.1016/0304-8853\(83\)90545-0](http://dx.doi.org/10.1016/0304-8853(83)90545-0)
- [9] Lynn, J.W., Raggazoni, A., Pynn, R. and Joffrin, J. (1981) Observation of Long Range Magnetic Order in the Reentrant Superconductor  $\text{HoMo}_6\text{S}_8$ . *Journal de Physique Lettres*, **42**, 45-49.  
<http://dx.doi.org/10.1051/jphyslet:0198100420204500>
- [10] Morales, F., Escudero, R., Briggs, A., Monceau, P., Horyn, R., Le Berre, F. and Pena, O. (1996) Point Contact Spectroscopy on the Ferromagnetic Superconductor  $\text{HoMo}_6\text{S}_8$ . *Physica*, **218B**, 193.  
[http://dx.doi.org/10.1016/0921-4526\(95\)00591-9](http://dx.doi.org/10.1016/0921-4526(95)00591-9)
- [11] (1982) Superconductivity in Ternary Compounds II. In: Maple and Fischer, Eds., Springer-Verlag, Berlin.
- [12] Lynn, J.W., Shirane, G., Thomlinson, W., Shelton, R.N. and Moncton, D.E. (1981) Magnetic Properties of the Reentrant Ferromagnetic Superconductor  $\text{HoMo}_6\text{S}_8$ . *Physical Review B*, **24**, 3817.  
<http://dx.doi.org/10.1103/PhysRevB.24.3817>
- [13] Bardeen, J., Cooper, L.N. and Schrieffer, J.R. (1957) Theory of Superconductivity. *Physical Review*, **108**, 1175.  
<http://dx.doi.org/10.1103/PhysRev.108.1175>
- [14] Zubarev, D.N. (1960) Double-Time Green Functions in Statistical Physics. *Soviet Physics Uspekhi*, **3**, 320.  
<http://dx.doi.org/10.1070/PU1960v003n03ABEH003275>
- [15] Ishikawa, M., Fischer, O. and Muller, J. (1978) Long Range Magnetic Order in the Superconducting State of Heavy Rare Earth Molybdenum Sulfides and Their Pseudo Ternary Compounds. *Journal de Physique*, **39**, C6-1379.

Scientific Research Publishing (SCIRP) is one of the largest Open Access journal publishers. It is currently publishing more than 200 open access, online, peer-reviewed journals covering a wide range of academic disciplines. SCIRP serves the worldwide academic communities and contributes to the progress and application of science with its publication.

Other selected journals from SCIRP are listed as below. Submit your manuscript to us via either [submit@scirp.org](mailto:submit@scirp.org) or **Online Submission Portal**.

