



Determination of the Content of Impurity Elements in Aluminum Alloy by XRF Analysis

Jing Zhou, Jie Shi, Bo Zhang, Shaoqin Li

School of Nuclear Technology & Automation Engineering, Chengdu University of Technology, Chengdu, China

Email: zjg1809424@163.com

How to cite this paper: Zhou, J.G., Shi, J., Zhang, B. and Li, S.Q. (2021) Determination of the Content of Impurity Elements in Aluminum Alloy by XRF Analysis. *Open Access Library Journal*, 8: e7836. <https://doi.org/10.4236/oalib.1107836>

Received: August 5, 2021

Accepted: August 27, 2021

Published: August 30, 2021

Copyright © 2021 by author(s) and Open Access Library Inc.

This work is licensed under the Creative Commons Attribution International License (CC BY 4.0).

<http://creativecommons.org/licenses/by/4.0/>



Open Access

Abstract

Aluminum alloy is one of the most widely used metal materials in today's society. Measurement and analysis of its impurity elements can effectively improve the performance of aluminum alloy. Energy dispersive X-ray fluorescence spectrometry (EDXRF) was used to analyze the types and contents of impurity elements in aluminum alloys, and the best working conditions for the EDXRF analyzer to measure impurity elements in aluminum alloys were determined. The absorption and enhancement effect of Al, Zn, Cu on impurity elements in Ti, Cr, Mn, Fe, Cu, Zn in aluminum alloy was discussed, and the empirical coefficient method was used to correct it. The analytical precision of EDXRF was evaluated. The data show that the average relative errors of the impurity elements in the aluminum alloy are Ti: 7.50%, Cr: 2.48%, Mn: 0.99%, Fe: 3.49%, Cu: 0.44%, Zn: 0.14%, respectively. It shows that the XRF measurement method is feasible and the accuracy meets the requirements of engineering design.

Subject Areas

Nuclear Technology and Application

Keywords

Aluminum Alloy, Impurity Elements, XRF Analysis, Absorption-Enhancement Effect

1. Introduction

Aluminum alloy material, as one of the most important metal materials in today's society, has the advantages of low density, corrosion resistance, good elec-

trical conductivity and decoration. They have important applications in the fields of machinery, electronics, aerospace and equipment manufacturing [1]. The performance of aluminum alloy is determined by the content of aluminum and its other main elements, but some impurity elements will inevitably be mixed during the manufacturing process. When the content of impurity elements exceeds a certain level, it will also affect the performance of aluminum alloy. Therefore, the content of impurity elements in aluminum alloy has become one of the key parameters for evaluating the performance of aluminum alloy.

For the qualitative and quantitative analysis of the content of aluminum alloys element, there are mainly chemical analysis methods and instrumental analysis methods. The instrumental analysis method is mainly electron-coupled plasma atomic emission spectrometry (ICP-AES) [2] [3], which can realize simultaneous analysis of multiple elements with low detection limits, but the instruments are expensive, maintenance costs are high, and analysis speed is slow; chemical analysis methods need to use chemical reagents, which will damage the sample to be tested during the analysis process; the analysis speed is slow, and some chemical reagents are toxic, which will harm the operators. Energy dispersive X-ray fluorescence spectrometry has the advantages of good precision, multi-element online measurement, fast analysis speed, no sample making, and non-destructive analysis, which has a very broad application prospect in the analysis of alloy materials [4] [5] [6]. In recent years, many researchers have also carried out the measurement of the main elements of aluminum alloy by X-ray fluorescence spectrometry in order to measure the content of impurity elements in aluminum alloy.

2. Basic Theory

2.1. Qualitative and Quantitative Analysis

According to Moseley's law, when the primary X-ray irradiates the sample to be tested, the proportional relationship between the energy E_n of characteristic X-ray and the atomic number Z of element that emits the characteristic X-ray is:

$$E_n = -Rhc(Z - \sigma)^2 \left(\frac{1}{n_f^2} - \frac{1}{n_i^2} \right) \quad (1)$$

where R is the Rydberg constant, 1096.776 m^{-1} ; h is the Planck constant, $6.626 \times 10^{-34} \text{ J}\cdot\text{s}$; c is the speed of light, $3 \times 10^8 \text{ m}\cdot\text{s}^{-1}$; Z is the atomic number of the excited element; σ is the shielding coefficient; n_f and n_i are the number of electron shells.

Assuming that the elements in the sample to be tested are uniformly distributed, and the sample has an infinitely large smooth surface, the basic formula for the X fluorescence counting rate of the element to be tested can be expressed as:

$$I_k = \frac{KI_0}{\mu_0 + \mu_k} C \quad (2)$$

where I_0 is the intensity of the primary X-ray; μ_0 is the attenuation coefficient of the incident X-ray; μ_k is the attenuation coefficient of the characteristic X-ray; C is the element content; when the measurement conditions and the measurement object remain unchanged, the K value remains unchanged.

2.2. Correction of Matrix Effect

When the detection device is confirmed, the value of KI_0 of the specific element is determined in formula (2), but the value of $\mu_0 + \mu_k$ will change due to the matrix effect of the sample. The matrix effect mainly includes absorption-enhancing effect, non-uniform effect, surface effect and chemical valence effect. The sample used in the experiment is a cylindrical solid alloy sample, and the surface is polished, so the main consideration is the influence of the absorption-enhancement effect caused by the different composition of the sample. In the measurement of impurity elements in aluminum alloys, the sample to be tested contains a variety of elements, which causes the absorption-enhancement effect to be particularly significant. Therefore, when calculating the content of impurity elements, it is necessary to correct the influence caused by it. After obtaining the count rate of aluminum alloy sample, through polynomial fitting of count rate and content, the correction equation of impurity element content and its count rate is obtained:

$$W_i = A_0 + B_0 I_0 + B_1 I_1 + \dots + B_n I_n \quad (3)$$

where W_i is the content of the element to be measured; $A_0, B_0, B_1 \dots B_n$ are empirical coefficients, which are obtained by multiple linear regression; I_0 is the fluorescence intensity of the element to be measured; $I_1 \dots I_n$ are the characteristic X-rays intensity of the corresponding interfering element; n is the number of correction element.

3. Experimental Conditions

3.1. Experimental Instrument

The instrument used for the measurement is the desktop X-fluorescence analyzer Epsilon1 produced by Malvern Panalytical, Netherlands. The temperature and pressure sensors are set inside to compensate for changes in the atmosphere to ensure high quality and high sensitivity. The X-ray tube voltage can reach 50 keV with thin-window Ag anode, which is suitable for exciting heavy elements. It can realize the rapid online measurement of major, trace and trace elements from sodium to americium, and the detection limit LLD reaches 1 ppm-100%.

3.2. Determination of X-Ray Tube Working Conditions

The count rate and peak-to-back ratio of the element to be measured are mainly used as the selection criteria for determining the best working conditions of the X-ray tube, while considering the power of the X-ray tube and the maximum allowable relative error of the measurement. In the experiment, the method of

controlling variables is used to determine the parameters of filter, optimal tube voltage, and optimal tube current in sequence. The samples used and the measurement position remains unchanged. The final selected parameters are shown in **Table 1**. Under the premise of not affecting the experimental accuracy, try to increase the value of the count rate and reduce the relative error. The relative errors of the six elements to be measured are: Ti, Cr: 1.27%, Mn: 1.89%, Fe: 0.33 %, Cu: 1.58, Zn: 2.12%.

4. Discussion of Experimental Results

The measured samples are cylindrical solid aluminum alloy samples ($\Phi 4$ cm \times H3 cm). After polishing, the surface is smooth and flat, which can overcome the surface effect, non-uniformity effect and chemical valence effect. In the X-ray fluorescence analysis of aluminum alloys, the method of multiple regression is mainly used to correct the absorption-enhancement effect of each element to be measured of the aluminum alloy.

The K_{α} characteristic X-ray energies of Ti, Cr, Mn, Fe, Cu, and Zn are 4.51 keV, 5.41 keV, 5.895 keV, 6.40 keV, 8.04 keV, 8.63 keV, which are all larger than the K absorption limit of Al of 1.49 keV. For the quantitative analysis of impurity elements in aluminum alloy samples, correction is mainly made to the absorption effect of Al. Secondly, the characteristic X-ray energy of Cu is close to the K_{α} absorption limit of Mn and Fe, which will produce a more obvious enhancement effect. Therefore, the correction of Mn and Fe needs to be added to the correction of the enhancement effect of Cu. In the same way, the characteristic X-ray energy of Zn is close to the K_{α} absorption limit of Cu. When calculating the content of Cu and Zn, the absorption-enhancement effect needs to be corrected for each other.

It can be seen from **Table 2** that the average relative error of Ti element is 7.50%, the average relative error of Cr element is 2.48%; it can be seen from **Table 3** that the average relative error of Mn element is 0.99%, and the average relative error of Fe element is 0.99%. It can be seen from **Table 4** that the average relative error of Cu element is 0.44%, and the average relative error of Zn element is 0.14%. In the pure aluminum sample, the impurity element content is low, and the relative error is several times or even dozens of times that of the 6-series samples.

Table 1. Optimal pipe pressure and pipe flow in different measurement intervals.

Measuring range	Optimal tube voltage (keV)	Optimal tube current (μ A)	Filter
Na-Si	17	75	-
K-V	20	182	Al50
Cr-Co	21	98	Al50
Ni-Mo	46	98	Al50

Table 2. Binary regression analysis results of Ti and Cr.

Sample serial number	Ti				Cr			
	Theoretical value (%)	Fitted value (%)	Absolute error (%)	Relative error (%)	Theoretical value (%)	Fitted value (%)	Absolute error (%)	Relative error (%)
1	0.017	0.01764	0.0006	3.75	-	-	-	-
2	0.018	0.01941	0.0014	7.85	-	-	-	-
3	0.015	0.01393	-0.0011	-7.13	-	-	-	-
4	0.040	0.03954	-0.0005	-1.15	0.217	0.2230	0.0060	2.74
5	0.048	0.03995	-0.0081	-16.78	0.171	0.1626	-0.0084	-4.93
6	0.066	0.06958	0.0036	5.43	0.198	0.1981	0.0001	0.05
average	0.034	0.03334	0.00255	7.50	0.195	0.1946	0.0048	2.48

Table 3. Ternary regression analysis results of Mn and Fe.

Sample serial number	Mn				Fe			
	Theoretical value (%)	Fitted value (%)	Absolute error (%)	Relative error (%)	Theoretical value (%)	Fitted value (%)	Absolute error (%)	Relative error (%)
1	0.598	0.5956	-0.0024	-0.41	0.175	0.1768	0.0018	1.00
2	0.975	0.9719	-0.0031	-0.32	0.139	0.1449	0.0059	4.23
3	0.973	0.9753	0.0023	0.23	0.14	0.1414	0.0014	1.00
4	0.058	0.0594	0.0014	2.38	0.377	0.3997	0.0227	6.01
5	0.098	0.0847	-0.0133	-13.53	0.512	0.4937	-0.0183	-3.58
6	0.387	0.3950	0.0080	2.06	0.172	0.1693	-0.0027	-1.59
average	0.515	0.5137	0.0051	0.99	0.253	0.2543	0.0088	3.49

Table 4. Ternary regression analysis results of Cu and Zn.

Sample serial number	Cu				Zn			
	Theoretical value (%)	Fitted value (%)	Absolute error (%)	Relative error (%)	Theoretical value (%)	Fitted value (%)	Absolute error (%)	Relative error (%)
1	4.371	4.3672	-0.0038	-0.09	0.039	0.0391	0.0001	0.26
2	0.081	0.0812	0.0002	0.26	0.005	0.0059	0.0009	18.38
3	0.081	0.0804	-0.0006	-0.75	0.004	0.0050	0.0010	25.05
4	0.035	0.0471	0.0121	34.56	0.021	0.0236	0.0026	12.45
5	0.26	0.2492	-0.0108	-4.15	0.1	0.0969	-0.0031	-3.08
6	1.777	1.7755	-0.0015	-0.09	5.792	5.7926	0.0006	0.01
average	1.101	1.1001	0.0048	0.44	0.994	0.9939	0.0014	0.14

5. Conclusion

The content of impurity elements Ti, Cr, Mn, Fe, Cu, Zn in 6 series of aluminum alloys was analyzed and studied by EDXRF method. The best working conditions for the analysis of different impurity elements in aluminum alloy by Mal-

vern Panalytical desktop Epsilon1 X fluorescence analyzer system were determined, and the influence of matrix effect in the EDXRF method was corrected by the empirical coefficient method. After the content of the sample, the mathematical model and linear regression equation between the content and the counting rate in the aluminum alloy sample are established for different impurity elements. The binary regression method is used for Ti and Cr, and the ternary regression method is used for Mn, Fe, Cu, Zn for matrix correction. It has greatly improved the measurement accuracy of impurities in the 6 series aluminum alloys. The average relative errors are Ti: 7.50%, Cr: 2.48%, Mn: 0.99%, Fe: 3.49%, Cu: 0.44%, and Zn: 0.14%. The results show that the measurement error of the aluminum alloy impurity elements is small within the detection limit, and the XRF measurement method can meet the analysis requirements of aluminum alloy impurity elements in industrial production.

Acknowledgements

Thanks for my junior brothers and sisters, Jiang Yunrui and Shi Jie, who give a lot of help in the experiment. Thanks to our school for providing me with a place to experiment.

Conflicts of Interest

The authors declare no conflicts of interest.

References

- [1] Santa Coloma, P., Izagirre, U., Belaustegi, Y., *et al.* (2015) Chromium-Free Conversion Coatings Based on Inorganic Salts (Zr/Ti/Mn/Mo) for Aluminum Alloys Used in Aircraft Applications. *Applied Surface Science*, **345**, 24-35. <https://doi.org/10.1016/j.apsusc.2015.02.179>
- [2] Vanhaecke, F., Riondato, J., Moens, L. and Dams, R. (1996) Non-Spectral Interferences Encountered with a Commercially Available High Resolution ICP-Mass Spectrometer. *Fresenius' Journal of Analytical Chemistry*, **355**, 397-400. <https://doi.org/10.1007/s0021663550397>
- [3] Szalóki, I., Patkó, J. and Papp, L. (1990) Determination of Cr and Mn in Aluminium Wires and Sheets by XRF, NAA and AAS. *Journal of Radioanalytical and Nuclear Chemistry*, **141**, 279-287. <https://doi.org/10.1007/BF02035795>
- [4] Bertin, E.P. (1975) Principles and Practice of X-Ray Spectrometric Analysis. Plenum Press, New York, London. <https://doi.org/10.1007/978-1-4613-4416-2>
- [5] Mzyk, Z., Anyszkiewicz, J. and Matusiak, H. (2012) Analysis of Alloy Composition by X-Ray Fluorescence Spectrometry Using Liquid and Thin Layer Techniques with an Internal Standard. *Spectrochimica Acta Part B*, **69**, 44-49. <https://doi.org/10.1016/j.sab.2012.03.004>
- [6] Sarbajna, C., Durani, S., Nayak, S., *et al.* (2013) Determination of U, S, V, Cu, Zn, Sr, Mo and Ce in Carbonate Rocks by Wave Length Dispersive X-Ray Fluorescence Spectrometry and Inductively Coupled Plasma Optical Emission Spectrometry. *Atomic Spectroscopy*, **34**, 31-38. <https://doi.org/10.46770/AS.2013.01.006>